

DYNAFERRO

CODE:22.4--

DESCRIPTION

Primer paint for metallic surfaces formulated with iron oxide and alkyd resins obtaining thus a good quality/price relationship product.

USE INTERIOR- EXTERIOR

Antirust primer for iron that can be repaint with a large range of synthetic enamels, both industrial and decorative.

FEAUTURES

	Finish	Semi-matt
w	Color	Grey, Oxyde red, black.
w	Viscosity	30+minimum S/FR1007
w	Density	1,62 +/- 0,1 gr/cc, s/FR 1001
w	Drying	6-8 hours to the touch
	Repaint	40 minutes to the touch. Repaint: Minimum 6 hours; maximum: 8 hours.
w	Thinner	D-17 (XL)
w	Performance ..	8m2/l/coat
	Content of COV	Minimum 500 g/l.



INDUSTRIAS JUNOS.A.

Bº URIOSTE, 64. 48.530 ORTUUELLA (BIZKAIA) TEL: 94 664 15 11 FAX 94 664 17 53
E-MAIL: pinturasmarina@juno.es

SURFACES PREPARATION

Steel and iron

Steel surfaces have to be rough and free of grease stains, rubber, dust, oxide and mill scaling. To obtain a good antirust protection, it is recommended to sand-jet the surfaces until reaching SA 2 1/2 grade.

APPLICATION

Paint brush or paint roller: normal use or diluted with 5% D-17- XL.
Paint gun: diluted with 10-15% D-17 XL

CLEANING

D-17 Solvent (XL) or Universal Solvent

COMMENTS

Stir well until completely homogeneous

PRESENTATION

Metallic lithographic can: sizes: 5 and 20 kilos.

N.B: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, they must only be interpreted as indications **WITHOUT LIABILITY** even in regard to possible third -party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes . The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



INDUSTRIAS JUNOS.A.

Bº URIOSTE, 64. 48.530 ORTUUELLA (BIZKAIA) TEL: 94 664 15 11 FAX 94 664 17 53

E-MAIL: pinturamarina@juno.es