

TECHNICAL DATA SHEET

J-300 Vinyl Soft Sheen

Code: 71055

JANUARY 2015

DESCRIPTION

J-300 Vinyl Soft Sheen is a premium quality, durable mid sheen emulsion suitable for all normal interior wall and ceiling surfaces. This high quality washable paint is based on the latest generation vinyl copolymers available giving an excellent mid sheen that withstands normal levels of humidity and can be wiped clean. Use on interior walls and ceilings as an attractive alternative to silk and matt finishes.

RECOMMENDED USE: INTERIOR

Suitable for interior use on all normal wall and ceiling surfaces. Suitable for use on plaster, wallboards, concrete, cement rendering, brickwork and blockwork etc. Ideal for anywhere a protection against atmospheric agents and humid environments is required. Product tolerates the levels of atmospheric humidity present in normal interior environments and will withstand moderate washing/cleaning. J-300 is

APPLICATION

- Brush, roller or spray.
- Stir the recipient contents thoroughly until evenly mixed.
- Dilution: Dilute with water, up to 20 - 25 % in volume.
- All surfaces to be painted should be clean, dry and free from loose and flaking material. Prime bare surfaces with appropriate JUNO Primer. Rub down previously gloss painted surfaces with fine waterproof abrasive paper and rinse thoroughly.
- Avoid the inhalation of dust. Wear a suitable face mask if dry sanding.
- Do not apply on substrates with temperatures below 5°C, or overly heated.
- Dying: Use water-based Junoral Water or Universal Juno colorants, not

OBSERVATIONS

In case of mould, fungus, algae or other parasite contaminations, take the following steps:

- Wash with 10 % bleach and water solution.
- Rinse with water
- Use ANTI-MOULD products.

If saline efflorescence (saltpetre) is found:

- Brush and wash with 10% Hydrochloric Acid or 10% Zinc Sulphate solution.
- Rinse with water.
- Allow to dry thoroughly before painting.

These operations must be carried out under appropriate safety conditions.

APPLICATION PROCEDURE

SUBSTRATE	PREPARATION	APPLICATION	
		INTERIOR	EXTERIOR*
Concrete, cement or mortar based on NEW hydraulic binders.	Cleaning Efflorescence removal	1 Coat of Hidrocril diluted * 2 Coats of J-300 diluted with 10% water	* 1 Coat of Junolite Façades. * 2 Coats of J-300 diluted with 10% water
Non-pulverous old paints	Cleaning and/or washing	* 2 Coats of J-300 diluted with 10% water	* 2 Coats of J-300 diluted with 10% water
Pulverous paints	Cleaning. Fix	* 1 Coat of Hidrocril diluted. * 2 Coats of J-300 diluted with 10% water	* 1 Coat of Akрил 80. * 2 Coats of J-300 diluted with 10% water
Old paint in poor condition.	Remove. Sandblasting or Juno Paint Remover	Same as new surfaces	* Same as new surfaces
Plaster, gypsum	Cleaning. Fix if necessary	* 1 Coat of Hidrocril diluted. * 2 Coats of J-300 diluted with 10% water	* Not recommended.

Finish: Satin

Color: White.

Density: 1, 40 ± 0.05 S/FR1001

Viscosity: Minimum 75 P S/FR1007

**Drying time: 45 minutes to the touch
Repaint minimum 24 hours.
Maximum: undefined.**

VOC's content: Maximum 30 g/l.

Performance: 9-11 m2 / L/ coat

Flash point: Non-flammable

Solids in volume: 40 (±2) % Theoretical

**Wet rubbing resistance:
Over 1.000 cycles. UNE 48 - 284**

*If with climatic conditions our recommendation sealing the surfaces with AQUA-SEAL Code 21203. The information contained in this data sheet has been prepared in good faith and to the best of our knowledge. However, they must only be interpreted as indications WITHOUT LIABILITY even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes. The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.

I-300 Vinyl Soft Sheen

APPLICATION RECOMMENDATIONS

Surfaces must be clean of dust, grease, oils, dirt, rust, waste or anything else that may contaminate the paint.

Remove the paint, varnishes or old treatments in a poor state and if needed clean up the imperfection, area and exposition with an adequate filler. Shake the container before application to homogenize the paint and the color.

Respect the recommended application temperature and the drying times between coats (20°C, relative humidity 65%). The thickness of application, temperature and humidity may affect drying times.

Buy only the necessary quantity required, taking into account the m², porosity and support texture. Work with the appropriate ventilation and respect the safety precautions norms indicated in the safety data

SHIPPING



Packaging: 04/10/15 liters

Shipping Weight:

Units per pallet: 120/33/33

Freight Classification:

Paint or paint related material



Transport Information

No restriction for transport (ADR/RID, IMDG, IATA)



CLEANING

Remove as much product as possible from application equipment before cleaning.

Replace lid firmly.

Clean equipment immediately after use with warm soapy water and rinse thoroughly.

Some local authorities have special facilities for the disposal of waste coatings.

Do not empty product into drains or watercourses.

Store the remaining product in a dry and

The information contained in this data sheet may vary and must be updated. Please visit www.juno.es or consult with your nearest JUNO representative who will provide you with the most recent data sheet. Our technical instructions and advice whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, they must only be interpreted as indications WITHOUT LIABILITY even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes. The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.