

PINTURAS JUNO

DATA SHEET

PLASTE FIBRA

CODE: 77250

DESCRIPTION

Aqueous glass fibre reinforced elastic filler.

USAGE: INDOOR - OUTDOOR

Suitable for filling, sealing and restructuring of fine and major cracks on surfaces such as gypsum, cement, wood, plastic coatings, etc. avoiding the need for glass fibre.

CHARACTERISTICS

- Binding: acrylic copolymers
- Diluent..... Water
- Density: 1.2 +/-0.05 g/cc
- Drying time: 2 – 24 hours, according to the substrate thickness and atmospheric conditions.
- Universal or water-based colorants can be used at 4% max.
- Elastic and waterproof.
- It can be sanded down once dry
- Ageing resistance.
- Excellent adherence for all types of substrate: gypsum, wood, polystyrene, concrete, etc.
- Maximum coat thickness: 0-2/0-3 m/m

APPLICATION PROCEDURE

Substrates must be clean, dry, treated and free of dust, grease and wax.

Remove dust and treat and prime surface.

Isolate and protect metallic surfaces with a metal primer.

If deep cracks are found: widen cracks, remove the dust and prime with **Hidrocril** diluted with 4 parts of water; and apply **Plaste Fibra** with a spatula avoiding the formation of any air pockets. Once dry, retouch if necessary. Sand-down and finish off.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION INSTRUCTIONS

Use a trowel or a spatula.

CLEANING

Clean any product excess and all tools with water.

Surfaces must be dry, clean, healthy and ready to support loads.

Take into account any pulverous or detachable bases beforehand.

PRECAUTIONS

Do not apply in full sun or in temperatures below 5° C.

Do not use on surfaces permanently exposed to moisture.

STORAGE

Keep indefinitely perfectly closed in its original container and protect from extreme temperatures.

SAFETY

Exempt from safety labelling.

PACKAGING

Plastic container. Size: 1 kg

Date: January 2,003/Revision: 2

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es