

PINTURAS JUNO

DATA SHEET

MEDITERRANEAN FAÇADES

CODE: 73312

DESCRIPTION

An acrylic coating based on a synthetic resin emulsion (acrylic styrene copolymer), high -stability pigments and additives, which provides easy handling and a continuous surface.

USAGE: INDOOR - OUTDOOR

This continuous coating is suitable for the protection and decoration of façades in mild climates and indoor decoration of storages, staircases, etc.

CHARACTERISTICS

• Finish	Smooth/matt
• Colour	White
• Viscosity	Min 180 Poises S/FR1007
• Density	1.80 +/-0.05 S/FR1001
• Drying time	To the touch: 2 hours Second coat: Minimum 12 hours Maximum: Indefinite
• Diluent	Water
• Solids in volume	(55+/-2)% Theoretical
• Coverage	6 m ² / Lt / coat
• Health & Safety	Aqueous-phase paint product: Exempt from labelling
• VOC content	Max 30 g/l

APPLICATION INSTRUCTIONS

- Brush, roller or spray gun.
- Pneumatic equipment.
- Stir the recipient contents thoroughly until evenly mixed.
- Apply on clean, dry and consolidated surfaces.
- Do not apply on substrates with temperatures below 5°C, or excessively heated.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION PROCEDURE

SUBSTRATE	PREPARATION	APPLICATION	
		INDOOR	OUTDOOR
Concrete, cement or mortar, based on NEW hydraulic binders	Cleaning Efflorescence removal	* 1 Coat of Akрил 80 Varnish. *2 Coats of Mediterranean Façades diluted with 10% water	* 1 Coat of Akрил 80 Varnish. *2 Coats of Mediterranean Façades diluted with 10% water
Non-pulvurent old paints	Cleaning and/or washing	*2 Coats of Mediterranean Façades diluted with 10% water	*2 Coats of Mediterranean Façades diluted with 10% water
Old pulvurent paints	Cleaning. Fix	* 1 Coat of Hidrocril diluted. *2 Coats of Mediterranean Façades diluted with 10% water	* 1 Coat of Hidrocril diluted. *2 Coats of Mediterranean Façades diluted with 10% water
Old paint in poor condition.	Remove. Sandblasting or Juno Paint Remover	* Same as new surfaces	* Same as new surfaces
Plaster, gypsum	Cleaning. Fix if necessary	* 1 Coat of Hidrocril diluted. *2 Coats of Mediterranean Façades diluted with 10% water	* Not recommended.

OBSERVATIONS

For all types of substrate:

In case of mould, fungal, algae or other parasite contaminations, take the following steps:

- Wash with 10% bleach and water solution .
- Rinse with water.
- Allow to dry thoroughly before painting.
- Prime with **Junosan Base Cleaner** .
- Use ANTI-MOULD products.

If saline efflorescence (saltpetre) is found:

- Brush and wash with 10% Hydrochloric Acid or 10% Zinc Sulphate solution.
- Rinse with water.
- Allow to dry thoroughly before painting.

These operations must be carried out under appropriate safety conditions.

DYING

With **Junoral Water Colorant** , not exceeding 3% of colorant. With **Junokril** colours used as colorant.

PACKAGING

Lithographed plastic container. Sizes: 4 and 15 litres

Date: January 2007/Revision: 5

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Sacconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es