

Technical Datasheet

JUNOPLUS GLOSS

Prod.Code: 16000 Trim/Enamels



DESCRIPTION

High quality synthetic multipurpose matt alkyd based enamel. Gives an excellent tough and durable finish that keeps its color for longer and offers outstanding application and coverage. Matt finish is for interior use only, while satin and gloss finishes can be used on exterior surfaces.

USE: INTERIOR

Junoplus is a high quality interior/exterior enamel available in three different finishes (Gloss, Satin or Matt). Ideal for doors, windows & trim. Specially recommended for primed wood and metallic surfaces.

Junoplus Gloss is ideal for painting furniture.

PROPERTIES

- Junoplus Gloss is available in 22 ready to use colours which are tintable to any RAL colour.
- Maximum opacity and light/weather stability
- Seals pores minimizing surface dirt pick-up
- Long lasting gloss finish
- Excellent hiding power
- Excellent levelling and quick drying
- Does not crack or form blisters
- Excellent hardness and rub resistance
- Washable
- Fire Retardant

CERTIFICATIONS

- Fire retardant to : B-s1, d0. UNE 13501-1

Finish: Gloss

Colour: Junoplus Color Card and Junomatic Tinting Sys.

Viscosity: Minimum 160" S/FR1002

Density:

WHITE: 1,21 ± 0,05 g/cc S/FR1001
COLOURS: 1,05 ± 0,05 g/cc S/FR1001

Drying: Touch Dry in 8 hours

Min. Repaint time: 24 hours

Max. Repaint time: 8 days

Diluent: D-16 Thinner

Performance: 12 m²/L (35 dry microns)

Tinting: Juno Universal Colorant (max 2%)

Volume solids: 42 ± 2 %. Theoretical for white

Flash Point: Flammable from 32 °C

VOC Content: Maximum 300 g/l

16000 WHITE	16001 BLACK
16002 CHAMOIS	16003 BROWN
16004 GRASS GREEN	16005 IVORY
16006 TRAFFIC GREY	16007 OCHER
16008 BLUE	16009 AZUL ULTRAMAR
16010 RADIANT BLUE	16011 WAGON GREEN
16011 FIRE RED	16021 WAGON RED
16022 BLOOD RED	16029 MEDIUM YELLOW
16031 LIGHT GREY	16038 CLOUD GREY
16039 DARK GREY	16054 MEADOW GREEN
16058 MOSS GREEN	16069 ARABIA BROWN



Format: 0,750L / 4 L

The information contained in this data sheet may change and must be updated. Consult www.junopaints.com or your nearest JUNO representative to obtain the most recent data sheet. The technical advice of application, whether verbal, written or through trials, are based on the experience and technical knowledge of JUNO. The data shown in this document should be considered a recommendation and as such does not imply any commitment, even with regard to possible industrial property rights of third parties. The application, employment and transformation of the products supplied by JUNO are carried out by third parties. Consequently, the final result is the sole responsibility of the client, applicator or manipulator of the products and not of the supplying company. This document does not exempt the client from carrying out his own examination of the products supplied, in order to verify their suitability for the procedures and intended purposes. In case of responsibility assumed by JUNO, it will be limited to the strict value of the goods supplied and used by the customer, whatever the damages and losses caused. JUNO guarantees the quality of all its products, in accordance with the current General Sales Conditions.

Technical Datasheet

JUNOPLUS GLOSS

Prod.Code: 16000 Trim/Enamels



SURFACE PREPARATION

WOOD. Before applying Junoplus, make sure that surfaces are sound (i.e. not flaking) and sanded, clean, and completely dry. Humidity content of wood must be lower than 15%.

Prime using **Hangers Sealer (Prod. Code 21.000)** and sand the sealer lightly before applying Junoplus.

IRON & STEEL must be rust and grease-free. Make sure surface is completely clean and dry. Apply a coat of anticorrosive primer using **Metalex Primer (Prod. Code 27.000)**.

ALUMINIUM & GALVANIZED STEEL. When hot-dip galvanized surfaces are exposed to atmospheric conditions, they form zinc corrosion (whitish rust), and contaminants can accumulate. This must be removed by washing with clean water containing detergents and by using a scourer, followed by intensive cleaning with hot water. Alternatively, the use of hot water, pressurized water, steam cleaning, sweep blasting or cleaning with manual or mechanical tools may be suitable.

Properly dry the surface and apply a coat of **Multisupport primer. (Prod.Code 27040)**

MASONRY.

Untreated surfaces:

Must be dry and free from efflorescence. In case of cement or plaster neutralize with a mixture of water and Chloridic acid (to 10 %).

Prime using **Hangers Sealer (Prod.Code 21.000)**.

Painted Surfaces: If the painted surface is in good condition, Junoplus can be applied directly, after washing and smooth sanding to completely eliminate any gloss and surface tensions. Always carry out this operation to avoid cracking problems and to improve lack of adhesion. If the paint is in poor condition, remove it completely using **Junopaint Stripper (Prod.Code 83.100)**.

Clean up any residues and paint as on untreated surfaces.

APPLICATION TIPS

Stir contents until complete homogenization.

Apply on consistent, clean and dry surfaces.

Applying too thick coats may lead to finish problems, and can also cause problems with the drying process.

ENVIRONMENTAL CONDITIONS.

Do not apply at temperatures below 5°C, nor on excessively hot surfaces.

The temperature of the surface to be painted must be at least 3°C above the dew point.

The relative humidity should not exceed 80%.

APPLICATION METHOD.

Use special brush or roller for oil based products. Apply in thin layers using long brushstrokes to favour optimal drying conditions.

Do not surpass 30-35 micron thickness per coat. For spraying dilute with 15% **D-16 Thinner (Prod.Code 50.012)** Add the thinner while stirring.

Do not use any other types of thinners (f.ex. **D-17 or D-45**) as they may cause finish and drying problems.

CLEANING.

Clean stains and work tools immediately using JUNO's **D-16 Thinner (Prod.Code 50.012)** or JUNO's **D-45 - Universal Thinner (Prod.Code 50.017)**

OBSERVATIONS

Avoid applying in thick coats, above the indicated 30-35 microns, as this can lead to wrinkling, drying and repainting problems.

When painting red, yellow or orange toned colors, it is recommended to base coat with similar colors to achieve the best possible opacity. Junoplus is to be tinted using exclusively the JUNOMATIC System.

SAFETY & ENVIRONMENT

When dealing with a solvent based product ensure good air ventilation and employ proper protection measures.

Avoid sources of ignition. Minimize product waste by estimating the real amount needed, taking into account the m², porosity and texture of the substrate.

Store surplus material in a ventilated, dry place. The container must be clean and of adequate size for the quantity of product left over.

Close containers carefully and keep them upright to prevent spills.

Preserve containers from frost, high temperatures and direct exposure to the sun. Store unused product for new use and to reduce environmental effects.

Do not eat, drink or smoke during the preparation and application of the product. Surface preparation and application operations must be carried out with appropriate safety measures.

For more information consult the Material Safety Data Sheet. In case of contact with eyes, rinse with plenty of clean water. Keep out of the reach of children. Do not discharge into drains or the environment. Dispose to an authorized waste collection point. Consult your council about the correct recycling of both packaging and waste and leftover paint according to law and principles of environmental respect.

The information contained in this data sheet may change and must be updated. Consult www.junopaints.com or your nearest JUNO representative to obtain the most recent data sheet. The technical advice of application, whether verbal, written or through trials, are based on the experience and technical knowledge of JUNO. The data shown in this document should be considered a recommendation and as such does not imply any commitment, even with regard to possible industrial property rights of third parties. The application, employment and transformation of the products supplied by JUNO are carried out by third parties. Consequently, the final result is the sole responsibility of the client, applicator or manipulator of the products and not of the supplying company. This document does not exempt the client from carrying out his own examination of the products supplied, in order to verify their suitability for the procedures and intended purposes. In case of responsibility assumed by JUNO, it will be limited to the strict value of the goods supplied and used by the customer, whatever the damages and losses caused. JUNO guarantees the quality of all its products, in accordance with the current General Sales Conditions.