

Technical Data Sheet

AQUALAC GLOSS

Code: 10300 Enamels



DESCRIPTION

Water-based enamel with great coverage and excellent leveling. Product based on quick drying acrylic resins with extraordinary weather resistance.

USE: INTERIOR-EXTERIOR

AQUALAC provides unsurpassed hiding on interior trim and cabinets, and exterior trim and doors. It is recommended for use on properly prepared and primed interior wood, plaster and drywall and exterior doors and trim, masonry and metal. Added optional anti-bacterial agents provide hygienic finish for hospitals, infirmaries etc

FEATURES

- Stable and covering colours.
- Permanent whiteness
- Excellent leveling
- Outdoor resistance
- Washable
- Good hardness
- Low odor
- Quick drying
- Does not propagate fire - Fire retardant

CERTIFICATIONS

- Reaction to fire B-s1, d0, UNE 13501-1

Finish: Gloss

Colour: Junomatic system

Viscosity: 30P S/FR1007 MIN.

Density:

P BASE: 1,22 +- 0,05 gr/cc S/FR1001.

D BASE: 1,11 +- 0,05 gr/cc S/FR1001

TR, GL and RD BASES: 1,03 +- 0,05 gr/cc S/FR1001

Drying time: Touch dry: 1 hour

Min. re-coat time: 24 hours

Max. re-coat time: 8 days

Solvent: water

Performance: 10-12 m²/l (per coat)

Tinting: Tinting machine

VOC content: 130 g/l max

Flash-point Non flammable (>60°C).

10300 WHITE/ P BASE

10302 D BASE

10303 TR BASE

10304 GL BASE

10305 RD BASE



Packaging: 0,750 / 4 L

The information contained in this data sheet may vary and must be updated. Please visit www.juno.es or consult with your nearest JUNO representative who will provide you with the most recent data sheet. Our technical instructions and advice whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, they must only be interpreted as indications WITHOUT LIABILITY even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes. The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.

Industrias JUNO, S.A. • Barrio Sakoni, 10 • 48950 Erandio (Bizkaia) • Tel. 944 670 062 • export@juno.es • www.juno.es

June 2017 Rev. 04

1 / 2

Technical Data Sheet

AQUALAC GLOSS

Code: 10300 Enamels



JUNO

SURFACE PREPARATION

WOOD (interior). Do not use on cracked or fissured wood surfaces. Surfaces must be clean, completely dry, sanded and free of grease, dust or foreign agents. Its humidity content cannot exceed 15%. In interior areas, prime using Natursell primer (cod. 21.100) or Hanger primer (cod. 21.000) and gently sand before applying the enamel. For exterior treat surface with woodworm killer if necessary.

IRON AND STEEL: Remove grease, rust, wastes and foreign agents. Prime using Metalex antirust primer (cod. 27.000)

ALUMINIUM & GALVANIZED SURFACES. If hot galvanized surfaces have been exposed to the atmosphere, zinc corrosion can occur (white rust) and contaminants may accumulate. As a result, they should be removed by washing with clean, fresh water containing detergents and by using abrasive fiber brush, followed by cleaning with hot water. Alternatively, the use of hot water, pressurized water, steam cleaning, sweeping blasting or cleaning with manual or mechanical tools may be appropriate. Once the surface is completely dry, apply one coat of Waterprim primer (cod. 30006) or Multisupport primer (cod. 27.040).

PAINTED SURFACES: If previously painted surfaces are well-preserved they can be directly painted after cleaning and gently sanding them to remove gloss. Always perform this operation to avoid tensions, and lack of adherence. If the paint is in very poor condition, remove it completely and proceed as with new.

GENERAL RECOMMENDATIONS

Stir the content well until evenly mixed.

Apply on clean, dry and consolidate surfaces.

ENVIRONMENTAL CONDITIONS. Do not apply to substrates with a temperature less than 5 ° C or excessively hot surfaces.

The temperature of the substrate should be at least 3 ° C above the dew point. The relative humidity should not exceed 80%.

Do not apply with risk of rain or strong wind.

APPLICATION METHOD. Brush or enamel roller. stretch enamel well. In exterior spaces, it is recommended the application of two coats.

CLEANNING. Clean stains and working tools immediately after use. with soapy water.

OBSERVATIONS

Water based paints are extremely sensible to weather and surfaces conditions. To obtain good results, it is essential to apply under dry and tempered conditions. Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty/plaster all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with an appropriate primer.

SAFETY AND ENVIRONMENT

Minimize product waste estimating the amount needed, taking into account m², porosity and texture of the substrate.

Store the remaining material in a ventilated and dry space. The package must be clean and be the right size for the amount of surplus product.

Close containers carefully and kept upright to prevent leakage. Preserve packages from frost, high temperatures and direct sunlight. Reuse the unused product to give it a new use and reduce environmental effects.

Do not eat, drink or smoke during preparation and product application.

For more information check the MSDS.

In case of contact with eyes, rinse with clean water. Keep out of the reach of children.

Do not discharge into drains or the environment. Dispose to an authorized waste collection point. Contact your local council about the correct recycling of both the packaging as waste and leftover paint according to law and principles of environmental respect