

**METALLIC
ALUMIUM**

CODE:5.807

DESCRIPTION

Polyurethane resin enamel modified in combination with aluminum glitter

USE

Specially conceived as finishing for all kind of metallic surfaces. Good antirust features due to its waterproof and high humidity resistance properties.

FEAUTURES

Finishing		Metallic
w Colors		Aluminum RAL 9007
w Density		0,99 +/- 0,05 gr/cc, s/FR 1001
w Drying		2 hours to the touch
Repaint		24 hours
w Thinner		D-17 (gun) or D40 (brush)
w Content of COV ..		Maximum 500 g/l
Solids in volume		41% theoretical
Flashpoint		24°C aprox
Performance		16,25 m2/liter/ coat (25 microns)



INDUSTRIAS JUNOS.A.

Bº URIOSTE, 64. 48.530 ORTUELLA (BIZKAIA) TEL: 94 664 15 11 FAX 94 664 17 53

E-MAIL: pinturamarina@juno.es

SURFACES PREPARATION

If it is applied on primer surfaces, follow instructions to repaint the surface.
If it is applied directly on a metal or wood surface, clean the area until dust or grease is removed.

MODE OF USE

Brush application: diluted eventually with thinner D-40
Gun application: diluted with D-17 solvent until right application depending on the kind of gun employed.

CLEANING

D-17 or D-40 thinner

REPAINT

Repainting can be done using the same product or using acrylic Acro enamel. Repaint after 24 hours.

OBSERVATIONS

Stir well until completely homogeneous.

N.B: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, they must only be interpreted as indications **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes. The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



INDUSTRIAS JUNOS.A.

Bº URIOSTE, 64. 48.530 ORTUUELLA (BIZKAIA) TEL: 94 664 15 11 FAX 94 664 17 53

E-MAIL: pinturamarina@juno.es