

PINTURAS JUNO

DATA SHEET

YATES VARNISH

CODE: 42005

DESCRIPTION

This varnish is based on special resin and UV radiation screens to obtain a protective and decorative finish of the highest quality.

USAGE: INDOOR

Use as a finishing varnish on any kind of timber. Due to its water vapour permeability and high resistance to UV radiation and marine environment, is particularly suitable for wood subject to extreme weather conditions.

CHARACTERISTICS

- | | |
|------------------------------|---|
| • Finish | Gloss |
| • Colour | Slightly amber. |
| • Viscosity | Min. 80" S/FR1002 |
| • Density | 0.90 +/-0.05 S/FR1001 |
| • Drying time | To the touch: 6-8 hours
Second coat: Min: 24-48 hours
Maximum: 72 hours |
| • Diluent | D-16 or White Spirit. |
| • Solids in volume: | 40% theoretical |
| • Flash point | Flammable (21° - 55° C) |
| • VOC content: | Max 500 g/l |
| • Theoretical coverage | 12 m ² / L / coat |

SURFACE PREPARATION

TIMBER

Wood surfaces must be clean, dry, grease-free and sanded. Its humidity content must not exceed 20%.

It can be applied over old varnish as long as it is in good condition, but for best results fully removing varnish is recommended.

Prior impregnation of new timber surfaces with **Base Protector** is recommended.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION PROCEDURE

Brush and spray gun.
For spray painting, dilute with 10% of **D-16**

CLEANING

D-16 or **White Spirit**.

REPAINTING

Same product.

OBSERVATIONS

Stir the recipient contents thoroughly until evenly mixed.
Clean very resinous timber with D-50 Solvent beforehand to avoid drying problems.
Always apply varnish in fine, well-spread coats to obtain an even gloss and the appropriate thickness to allow the wood pores to close perfectly.

PACKAGING

Lithographed metal container. Sizes: **0.750/4** litres.

Date: January 2006/Revision: 4

NB: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es