

# Technical Datasheet

## AQUA VARNISH

**JUNO**

Prod.Code: 82410 Varnish & Wood Treatments/ Water-based Varnish

### DESCRIPTION

Special odourless water-based polyurethane varnish for parquet.  
Formulated with single component aliphatic polyurethane resins, providing a non-yellowing film with a high chemical resistance to wear.

### USE: INTERIOR

Recommended for all types of parquet and wood surfaces due to its ease of application. Quick drying, with high resistance to abrasion and easy cleaning.

### PROPIEDADES

- Gloss film finish
- Provides a closed pore finish avoiding dirt pick-up
- Easy application
- Great hardness
- High abrasion resistance
- Quick drying
- Easy cleaning

**Finish:** Gloss

**Colour:** IClear

**Viscosity:** Min. 25" S/FR1002

**Density:** 1,02 ± 0,05 gr/cc S/FR1001

**Drying:** Touch dry - 30 minutes

**Min. repaint time:** 4-6 hours

**Max. repaint time:** After 24 hours, it is advisable to sand between coats.

**Thinner:** Water

**Practical coverage:** 10-12 m<sup>2</sup>/L (per coat)

**Flash point:** Not flammable

**VOC Content:** Maximum 130 gr/ltr.

82410 CLEAR



Format: 0,750 L / 4 L

The information contained in this data sheet may change and must be updated. Consult [www.junopaints.com](http://www.junopaints.com) or your nearest JUNO representative to obtain the most recent data sheet. The technical advice of application, whether verbal, written or through trials, are based on the experience and technical knowledge of JUNO. The data shown in this document should be considered a recommendation and as such does not imply any commitment, even with regard to possible industrial property rights of third parties. The application, employment and transformation of the products supplied by JUNO are carried out by third parties. Consequently, the final result is the sole responsibility of the client, applicator or manipulator of the products and not of the supplying company. This document does not exempt the client from carrying out his own examination of the products supplied, in order to verify their suitability for the procedures and intended purposes. In case of responsibility assumed by JUNO, it will be limited to the strict value of the goods supplied and used by the customer, whatever the damages and losses caused. JUNO guarantees the quality of all its products, in accordance with the current General Sales Conditions.

Industrias JUNO, S.A. • Barrio Sakoni, 10 • 48950 Erandio (SPAIN) • Tel.: +34 944 670 062 • [infoweb@juno.es](mailto:infoweb@juno.es) • [www.junopaints.com](http://www.junopaints.com)

December 2016 Rev. 12

1 / 2

# Technical Datasheet

## AQUA VARNISH



**JUNO**

Prod.Code: 82410 Varnish & Wood Treatments/ Water-based Varnish

### PREPARACIÓN DE SUPERFICIES

**NEW TIMBER.** The wood must be free of grease, sanded, clean and completely dry. Its moisture content should not exceed 15%. It is recommended to pre-treat the wood with an insecticidal/fungicidal treatment before applying the undercoat or varnish. Very resinous woods must be previously cleaned with solvent **D-45 (Cod 50.017)** to avoid drying problems.

**PRE-VARNISHED TIMBER.** Product can be applied directly onto old varnish coating as long as it is in good condition. It is necessary to degrease the surface, sand lightly to remove any gloss, before proceeding to apply one or two coats of AQUA VARNISH - either as supplied or thinned out with 5% water. Sand between each coat. If the varnish is in poor condition, it is advisable to remove it completely by sanding, and clean the surface dust. Finish with two coats of varnish, thinned with 5% water. Sand between each coat.

### APPLICATION TIPS

Stir product well until complete homogenization.  
Apply on consistent, clean and completely dry surfaces.  
Dilute the product depending on the porosity and condition of the substrate.  
Apply the product with sufficient ventilation.

**ENVIRONMENTAL CONDITIONS.** Do not apply on surfaces with temperature of less than 5°C, nor on excessively warm substrates. Relative humidity should not exceed 80%. Do not apply when risk of rain or strong wind is present.

**APPLICATION METHOD.** Brush or roller. Once the surface is prepared, finish with 2-3 coats of unthinned AQUA VARNISH in well stretched coats, at intervals of 4-6 hours to avoid adhesion problems. On very porous surfaces, it may be convenient to apply more coats. If more than 24 hours elapse between each coat, it is advisable to sand lightly to promote adhesion.

**CLEANING.** Immediately clean stains and tools used with water. In case of already dried varnish, use acetone for cleaning tools.

### OBSERVATIONS

On light wood types, especially oak and chestnut, apply product in very well stretched coats to avoid sagging and high varnish thickness, as intense coloration/darkening of the wood can occur.  
Finished and dried coats on parquet can be stepped on after 12 hours.  
Cleaning with water or detergent can be done after 10 days.  
Do not lay carpets on varnished surfaces until after a week has passed.  
Clean surface with vacuum cleaner and wet mopping to maintain the varnish in perfect condition.  
Clean stains with a neutral cleaner.  
Do not use strong solvents or acidic or alkaline products.

### SAFETY & ENVIRONMENT

Minimize the waste of the product estimating the real quantity needed, taking into account the m<sup>2</sup>, the porosity and texture of the substrate to be coated. Store leftover material in a ventilated and dry place. The container must be clean and of a suitable size for the quantity of excess product. Close the containers carefully and keep them upright to avoid spills. Preserve containers away from frost, high temperatures and direct sun exposure. Reuse leftover products to save the environment.  
Do not eat, drink or smoke during the preparation and application of the product.  
Surface preparation and application operations must be carried out with the corresponding PPE and safety measures.  
For more information consult the Safety Data Sheet.  
In case of contact with eyes, wash with clean and abundant water. Keep out of the reach of children.  
Do not discharge into drains or the environment. Dispose of product at an authorized waste collection point.  
Consult your council about the correct recycling of both the packaging and waste and leftover paint according to law and principles of environmental respect.

The information contained in this data sheet may change and must be updated. Consult [www.junopaints.com](http://www.junopaints.com) or your nearest JUNO representative to obtain the most recent data sheet. The technical advice of application, whether verbal, written or through trials, are based on the experience and technical knowledge of JUNO. The data shown in this document should be considered a recommendation and as such does not imply any commitment, even with regard to possible industrial property rights of third parties. The application, employment and transformation of the products supplied by JUNO are carried out by third parties. Consequently, the final result is the sole responsibility of the client, applicator or manipulator of the products and not of the supplying company. This document does not exempt the client from carrying out his own examination of the products supplied, in order to verify their suitability for the procedures and intended purposes. In case of responsibility assumed by JUNO, it will be limited to the strict value of the goods supplied and used by the customer, whatever the damages and losses caused. JUNO guarantees the quality of all its products, in accordance with the current General Sales Conditions.

Industrias JUNO, S.A. • Barrio Sakoni, 10 • 48950 Erandio (SPAIN) • Tel.: +34 944 670 062 • [infoweb@juno.es](mailto:infoweb@juno.es) • [www.junopaints.com](http://www.junopaints.com)