

PINTURAS JUNO

DATA SHEET

JUNOLAC SATIN VARNISH

CODE: 42001

DESCRIPTION

This varnish contains synthetic resins and matting agents which enhance the natural beauty of timber.

USAGE: INDOOR

Especially suitable for wooden surfaces where a satin finish with waterproof, detergent, abrasion and alcoholic beverage resistant properties are required.

CHARACTERISTICS

- | | |
|------------------------------|--|
| • Finish | Satin |
| • Colour | Transparent, slightly yellowish. |
| • Viscosity | Min 50" S/FR1002 |
| • Density | 0.92 +/-0.05 S/FR1001 |
| • Drying time | To the touch: 4-5 hours Second coat: Minimum: 24 hours Maximum: 72 hours |
| • Diluent | D-16 or White Spirit. |
| • Solids in volume: | 35% theoretical |
| • VOC content: | Maximum: 500 g/l. |
| • Theoretical coverage | 8-10 m ² / Lt / coat |

SURFACE PREPARATION

TIMBER

Wooden surfaces must be clean, dry, grease-free and sanded. Its humidity content must not exceed 20%. Apply a pore-filler beforehand and follow with one or two varnish coats.

It can be applied over old varnish as long as it is in good condition, but for best results fully removing varnish is necessary.

If the previously applied varnish is in poor condition, fully remove it and treat as new timber.



PINTURAS JUNO

Bº Sacconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION INSTRUCTIONS

Brush, roller or spray gun.

For spray painting, dilute with 10 -15 % of **D-16**

CLEANING

D-16 Solvent or Universal Solvent

REPAINTING

Same product.

OBSERVATIONS

Stir the recipient contents thoroughly until evenly mixed.

Clean very resinous timber with D-50 Solvent prior to application to avoid drying problems.

Always apply varnish in fine, well-spread coats to obtain an even gloss and the appropriate thickness to allow the wood pores to close perfectly.

PACKAGING

Lithographed metal container. Sizes: **0.375/ 0.750 / 4** litres.

Date: January 2007/Revision: 4

NB: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and S apply Conditions.



PINTURAS JUNO

Bº Sacconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es