

TECHNICAL DATA SHEET

CHLORINATED RUBBER PRIMER

Code: 21.855

DECEMBER 2013

DESCRIPTION

Antirust chlorinated- rubber primer pigmented with zinc phosphate in combination with unsaponifiables plasticizers, offering good adhesion and excellent water resistance. Lead and chrome free. Designed as an anti-corrosive primer for steel. To be used in conjunction with JUNO chlorinated rubber finishes. Mainly for use on areas subject to corrosive and chemical laden atmospheres. Good resistance to acids and alkalis.

USAGE: INTERIOR- EXTERIOR

Recommended for the protection of exterior steel surfaces. Good adherence on galvanized steel. Ideal for chemical & sewage treatment plants and swimming pool plant rooms.

SURFACE PREPARATION

Steel surfaces: Preferably sandblasted to SA 2 ½ grade. Proper mechanical cleaning and degreasing is necessary. Remove slag and welds and polish the rough edges with emery. Galvanized non-oxidized surfaces: Mechanical cleaning and degreasing.

APPLICATION PROCEDURE

Preferably applied by brush, but can also be applied using suitable "airless" spray adjusted to required viscosity, or Airbrush gun. Dilute with D-40. Clean-up: Use D-40 diluent.

APPLICATION RECOMMENDATIONS

Surfaces must be clean of dust, grease, oils, dirt, rust, waste or anything else that may contaminate the paint. Remove old paint, varnishes or treatments in poor state and if needed clean up and repair any imperfections. Shake the container before application to homogenize the paint and the color. Respect the recommended application temperature and the drying times between coats (20°C, relative humidity 65%). The thickness of application, temperature and humidity may affect drying times. Buy only the necessary quantity required, taking into account the m², porosity and support texture. Store the remaining product in a dry and well-ventilated place. Work with the appropriate ventilation and respect the safety precautions norms indicated in the safety data sheet of the product.

CLEANING

Clean splash and stains immediately with soapy water or with an adequate solvent. Clean tools after use (brushes, rollers, pencils, machines etc.) and let them dry before storing. Consult your town council about the appropriate recycling method for the container, waste and excess paint, in accordance with the existing legislation and environmental protection principles.

Finish: Matt

Color: Grey

Density: 1,40 ± 0,05 S/FR1001

Drying time: dust-free 2 hours

Non-sticky: 7/8 hours.

Repaint minimum 18 hours. Second-coats: undefined.

Solids in volume: 41% theoretical

Diluent: D-40

Coverage: 10 m²/L/ coat (40 dry microns)

VOC content: 535 g/l.

Flashpoint: 25°C approximately.

Solids in volume: 43% Theoretical

Pigmented zinc phosphate content: 41,7%

Resistance to dry heat: Max. temperature 80°C.

SHIPPING



Packaging: 05/20 kg
Shipping Weight:
Units per pallet: 120/33



Freight Classification:
Paint or paint related material



Transport Information
UN NUMBER 1263

The information contained in this data sheet may vary and must be updated. Please visit www.juno.es or consult with your nearest JUNO representative who will provide you with the most recent date sheet. Our technical instructions and advice whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, they must only be interpreted as indications WITHOUT LIABILITY even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes. The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.