

# PINTURAS JUNO

## DATA SHEET

### JUNODUR SATIN VARNISH

CODE: 44002

#### DESCRIPTION

Single-component synthetic polyurethane-resin based varnish.  
It provides a satin, resistant and soft to the touch finish for any kind of wood.

#### USAGE: INDOOR

It is specifically designed for restoring and varnishing wood furniture.

#### CHARACTERISTICS

- |                              |   |
|------------------------------|---|
| • Finish .....               | Satin   |
| • Colour .....               | Colourless  |
| • Viscosity .....            | Min 70" S/FR1002  |
| • Density .....              | 0.87 +/-0.05 S/FR1001   |
| • Drying time .....          | To the touch: 4 hours<br>Second coat: Minimum 24 hours<br>Maximum 72 hours. |
| • Diluent .....              | <b>D-16 or White Spirit.</b>  |
| • Flash point .....          | Flammable (21° - 55° C)   |
| • Theoretical coverage ..... | 10-12 m <sup>2</sup> / Lt / coat  |
| • VOC content .....          | Max 500 g/l   |

#### SURFACE PREPARATION

Apply on perfectly clean and sanded down wood surfaces. Treating new surfaces with Base Protector is recommended. After 24 hours, apply one or two coats of **Junodur Varnish** diluted with 5% **D-16**, spreading the product evenly and sanding down between coats.

For already varnished surfaces, and if the varnish is in good condition, it is necessary to degrease the surface, sanding down lightly and apply one or two coats of varnish directly or diluted with 5% **D-16 Diluent**, sanding down between coats.

If the varnish is in poor condition, remove it and clean the surface, and finish off with two coats of **Junodur Varnish**, diluted with 5% of **D-16**, and sanding down between coats.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

## APPLICATION INSTRUCTIONS

Brush: Directly or diluted with 5 % **D-16**.  
Spray gun: Diluted with 15-20% of **D-16**.

## CLEANING

**D-16 Solvent or Universal Solvent**

## REPAINTING

Same product

## OBSERVATIONS

Clean very resinous woods **D-50 Solvent** prior to application.  
Stir the recipient contents thoroughly until evenly mixed.

## PACKAGING

Lithographed metal container. Sizes: 0.750 / 4 and 20 litres.

Date: January 2007/Revision: 4

---

NB: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



**PINTURAS JUNO**

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es