

PINTURAS JUNO

DATA SHEET

CASTOR THICK TEXTURED EXTRA

CODE: 74304

DESCRIPTION

This acrylic copolymer based paste formulation boasts excellent hardness, adherence and whiteness.

This soft thick textured matt finish conceals any substrate imperfections.

USAGE: INDOOR

Suitable for decoration of stairs, public places, offices, rooms, etc.

It contributes to easily achieve raised finishes of any kind.

CHARACTERISTICS

• Finish	Matt
• Colour	White
• Viscosity	Min 800 P S/FR1007
• Density	1.80 +/- 0.05 S/FR1001
• Drying time	4 hours
	Second coat: Minimum: 24 hours Maximum: Indefinite
• Diluent	Water
• Solids in volume:	(55+/-2)% Theoretical
• Flash point:	Non flammable
• Coverage	2-6 m ² / L /coat depending on the type of finish
• VOC content	Max 30 g/l

APPLICATION INSTRUCTIONS

Brush, roller or spray gun.

It can be applied with a wool roller as undercoat, diluted at 20% in water.

Once dry, spread the paste with a wool roller undiluted or slightly diluted, ensuring an even layer is formed. Then texture using a foam roller No. 3.

The droplet effect is achieved using pneumatic painting equipment.

The surface must be dry, clean and free from efflorescence.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION PROCEDURE

SUBSTRATE	PREPARATION	INDOOR APPLICATION
Concrete, cement or mortars based on NEW hydraulic binders	Cleaning Efflorescence removal	* 1 Coat of Hidrocril diluted. * 1 Coat of Castor Thick Texture Extra diluted with 20% water. * 1 Coat of Castor Thick Texture Extra
Non-pulverous old paints	Cleaning and/or washing	* 1 Coat of Castor Thick Texture Extra diluted with 20% water. * 1 Coat of Castor Thick Texture Extra
Old pulverous paint	Cleaning Fix	* 1 Coat of Hidrocril diluted. * 1 Coat of Castor Thick Texture Extra diluted with 20% water. * 1 Coat of Castor Thick Texture Extra
Old paint in poor condition.	Remove. Sandblasting or Juno Paint Remover	* Same as new surfaces
Plaster, gypsum	Cleaning Fix if necessary	* 1 Coat of Hidrocril diluted. * 1 Coat of Castor Thick Texture Extra diluted with 20% water. * 1 Coat of Castor Thick Texture Extra

OBSERVATIONS

For all types of substrate:

In case of mould, fungus, algae or other parasite contaminations, take the following steps:

- Wash with 10% bleach and water solution.
- Rinse with water.
- Prime with **Junosan Base Cleaner**.
- Allow to dry thoroughly before painting.
- Use ANTI-MOULD products.

If saline efflorescence (saltpetre) is found:

- Brush and wash with 10% Hydrochloric Acid or 10% Zinc Sulphate solution.
- Rinse with water.
- Allow to dry thoroughly before painting.

These operations must be carried out under appropriate safety conditions. Must be stored in frost protected environments.

Fine cracks, chips and defects on masonry surfaces must be retouched with Plaste Juno before painting.

DYING

Use water-based **Junoral Water** or **Universal Juno** colorants, not exceeding 3% of colorant.

PACKAGING

Lithographed metal container. Sizes: 4 and 15 litres

Date: January 2007 Revision:

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es